

DTEC 136SAF Textured Floor Film White AirFree

08/2020

Product Description

DTEC 136SAF Textured Floor Film is a monomer, white matt 170 μ , embossed PVC film with a clear solvent based AirFree acrylic adhesive, laminated on an one-sided clay-coated silicone paper liner. It comes with a directly printable anti-slip surface that doesn't need any overlamine and the PVC offers an excellent dimensional stability. Especially designed for indoor floorgraphic applications with anti-slippery character and scratch resistant surface for mid-term floor decoration and advertising like eg. airports, railway stations, shopping centers, on flat smooth surfaces. The AirFree adhesive is easier to apply and you save time on application as no air gets entrapped under the vinyl.

Technical data	
Facefilm	Monomeric PVC, embossed, highly stabilized
Thickness	170 micron
Adhesive	Clear solvent acrylic permanent adhesive, AirFree
Release liner	One-sided clay coated, silicon paper 135g/m ²
Adhesive strength	~ 7.0 N/cm
REACH compliant	Yes
Temperature range	- 20°C to + 80°C, application temp: > 10°C
Printability	Eco-solvent, UV, Latex inks
Shelf life	2 years when stored at 15 to 25°C and \pm 50 % relative humidity (in original packaging)
Durability	6 months outdoor, middle-European climate

Printing guidelines

Allow material to adapt to room conditions for 24 hours before printing.

Print conditions: Best results are obtained between 15-25°C and 35-60% RH. DTEC 136SAF Textured Floor Film is digitally printable with all common solvent, or eco-/mild-solvent, latex and UV-inks. The coated release liner ensures high quality & high resolution print results due to its moisture stability and its optimized thermal conduction. Print results will vary for different printer ink combinations. Ink restrictions and heater setting have to be set for specific printer ink combinations to obtain the best results. To achieve the best possible print quality, please make sure that the correct ICC profiles or printer settings are used.

Disclaimer

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test our products suitability for the purpose intended. The quality of our products is regularly examined, upgraded and developed. We reserve the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of their products in accordance with their latest knowledge.

